

Internal and external finish with a pearlescent effect

DATA SHEET

Container: 25 kg.

Composition of the product:

seasoned slaked lime and kaolin.

Dilution:

ready to use.

Features:

highly breathable.

Diluent: water.

Estimated consumption:

5-6 Kg./sqm. In two coats.

Usage: inside/outside

Background preparation: ECOTON STAR is used for the realization of finish on inner and outer plaster to lime putty. For better breathability, it is recommended to use Copemalt plaster. In case, you should place this product on a pre-existing plaster, it is recommended to apply it on the surface to treat our Ecogras smoothing, to get greater uniformity and breathability.

The surface must be clean, free from dust, dirt and any traces of oil, grease and wax, which should be removed by brushing or sanding the surface. If the outside temperature exceeds + 30 ° C, we advise against the application because the product has to be applied at ambient temperatures between + 5 ° C and + 30 ° C with no wind and no exposition to the sun. In this case, the wall must be adequately wet with water and the applied material protected with sunscreening towels.

Application: apply ECOTON STAR finish in two layers with a steel spatula to obtain a thickness of about 2mm and finish it subsequently with a trowel sponge soaked in water. The installation must be performed without interruption over the entire wall from corner to corner. Once the treated area get dry, brush it with a dry brush.

Storage: the material is preserved for 12 months from the date of production, in sealed containers, provided that they are not exposed to frost or heat sources. The applicator must not modify the product, in that case ET Events & Technologies S.r.l.s assumes no responsibility.



H318 Causes serious eye damage
H315 Causes skin irritation
H335 May causes respiratory irritation

P280 We recommend to wear gloves and protective clothing and to protect your eyes and face.
P301+P330+P331 IN CASE OF INGESTION: rinse your mouth. DO NOT cause vomit.
P305+P351+P338 IN CASE OF CONTACT WITH EYES: rinse accurately for several minutes. Remove the lenses if necessary and keep on rinsing.



UNI EN 998-1:2010