



www.etgc.it

MATERIALI ECOLOGICI PER L'EDILIZIA

COPEFIN A

Hearthenware finish

Earthenware finish and lime putty

DATA SHEET

Container: 18 kg.

Composition of the product:

Lime putty, earthenware.

Dilution:

Bicomponent.

Remove the divider inside the container, empty the earthenware bag into the mixture and mix everything energetically with a mixer, until you get a homogeneous dough.

If the mixture is still too thick, just add some water to make a workable mixture.

Features: 1mm granulometry.

Diluent: Water.

Estimated consumption:

Almost 6 Kg./mq. in two coats.

Usage: Inside/outside

Background preparation: The surface of the wall must be completely clean, without any trace of dust, dirt, oil, fat or wax, which should be removed by brushing or sanding. The product has to be laid at ambient temperature, between + 5 ° C and +30 ° C, with no wind and no exposition to the sun, otherwise the product needs to be wet and protect by suncreening towels.

Application: The final product is obtained by the sequent application of Copefin A and Copefin B. Firstly, spread Copefin A with a stainless steel trowel in two coats, with a theoretical yield of about 6 kg / sqm., with 1mm particle size. The product need to be spread, being careful that, between the two application, the underlying layer is kept wet. Secondly, being careful that the second application of Copefin A is wet, spread Copefin B.

Storage: The material is preserved for 12 months from the date of production, in sealed containers, provided that they are not exposed to frost or heat sources. The applicator must not modify the product, in that case ET Events & Technologies S.r.l.s assumes no responsibility.



H318 Causes serious eye damage
H315 Causes skin irritation
H335 May causes respiratory irritation

P280 We recommend to wear gloves and protective clothing and to protect your eyes and face.
P301+P330+P331 IN CASE OF INGESTION: rinse your mouth. DO NOT cause vomit.
P305+P351+P338 IN CASE OF CONTACT WITH EYES: rinse accurately for several minutes. Remove the lenses if necessary and keep on rinsing.



UNI EN 998-1:2010

ET Events & Technologies s.r.l.s. - Via Circonvallazione 22, Cassolnovo (PV) - Tel.0381 090518 - www.etgc.it